

POLİÜRETAN YARI MAT BOYA

POLYURETHANE SEMIDULL PAINT

ÖZELLİKLERİ

Yarı mat görünümlü, düzgün yüzey oluşturan, yüksek kapaticılık gücüne sahip, kimyasal maddelere, çizilmeye ve darbelerle karşı dayanıklıdır.

KULLANIM ALANLARI

Sararmaya karşı dirençli son kat mobilya mobilyasıdır.

Kaplama, MDF, masif, parke, rabitalarda ve mobilya sanayinde yüksek performans gösterir.

UYGULANACAK YÜZEYLERE ASTARLAMA İŞLEMİ

Eski boyalar temizlenir ve zımparalanır. Üzerine son kat boya işlemi uygulanır.

UYGULAMA

Hazırlanan yüzeye ağırlıkça 3 Birim A Komp. /1 Birim B Komp. olacak şekilde karıştırılır. Uygulama için hazırlanan karışım 4-6saat içinde kullanılıp bitirilmelidir. Uygulama yapılacak yüzeye önce bir toz şeklinde boya uygulaması yapılmalı, daha sonra uygun kalınlıkta uygulama yapılmalıdır. Tatbikat sıcaklığı +5 ile +35 °C arasında olmalıdır.

KURUMA SÜRELERİ (20 °C)

Dokunma Kuruması: 40-50 dk
Montaj Kuruması: 2-3 saat
Tam Kuruma: 24 saat

İNCELTME

Poliüretan tiner ile %15-25 oranında inceltilir. Uygulama için hazırlanan karışım 4-6 saat içinde bitirilmelidir.

BOYANABİLEN ALAN

Yaklaşık olarak 9-10 m²/lt (30-50 mikron uygulamada) alan boyanır.

PROPERTIES

Semidull-Looking , smooth surface, high covering capacity power, chemicals, scratch and impact resistant.

AREAS OF USE

Yellowing resistant finish furniture furniture. Veneer, MDF, solid wood, parquet, nexus and furniture industry shows in high performance.

APPLICABLE TO SURFACES PRIMING

Operation old paint are cleaned and make sure there are. On the last coat of paint process is implemented.

APPLICATION

Prepared surface by weight 3 units A Comp. /1 Unit B comp. mixed in such a way. Prepared mixture for the application 4-6 must be completed whether or not within the hour. Application will be made in the form of a powder to the surface before paint application has to be done, then it should be made on the implementation of the appropriate thickness. Exercise temperature should be between + 5 and + 35 ° c.

DRYING PERIOD (20°C)

Set to Touch Drying: 40-50 minutes
Montage Drying: 2-3 Hours
Hard Drying: 24 Hours

THINNING(VOLUME)

15-25% with polyurethane thinner. Prepared mixture for the application 4-6 must be completed within the hour.

COVERAGE

Approximately 9-10 m²/lt (30-50 mc single coat)



ÇİFT BİLEŞENLİ, ALİFATİK İSOSİYANAT KÜRLEMELİ, SARARMAYAN, UV DAYANIMI YÜKSEK FİZİKSEL VE KİMYASAL DİRENCİ YÜKSEK, KOLAY UYGULANABİLEN, İYİ YAPIŞAN VE YAYILAN POLİÜRETAN REÇİNE ESASLI YARI MAT BOYADIR.

TWO COMPENANT, THE CURED ALIPHATIC İSOSİYANAT, HIGH UV RESISTANCE PHYSICAL AND CHEMICAL RESISTANCE, EASY TO IDENTIFY APPLICABLE, , GOOD ADHESIVE AND SPREAD POLYURETHANE RESIN BASED SEMIDULL PAINT.

POLİÜRETAN ASTAR BOYA

POLYURETHANE PRİMER PAINT

ÖZELLİKLERİ

Parlak görünümlü, düzgün yüzey oluşturan, yüksek kapaticılık gücüne sahip, kimyasal maddelere, çizilmeye ve darbelerle karşı dayanıklıdır.

KULLANIM ALANLARI

Sararmaya karşı dirençli son kat mobilya mobilyasıdır.

Kaplama, MDF, masif, parke, rabitalarda ve mobilya sanayinde yüksek performans gösterir.

UYGULAMA

İyi bir yapışma elde etmek için yüzey tamamen temizlenmelidir. Yağ, pas ve kirlerden uygun temizlik malzemeleri ile arındırılmalıdır. Hazırlanan yüzeye ağırlıkça 3 Birim A Komp. /1 Birim B Komp. olacak şekilde karıştırılır. Uygulama için hazırlanan karışım 4 - 6 saat içinde kullanılıp bitirilmelidir. Uygulama yapılacak yüzeye önce bir toz şeklinde boya uygulaması yapılmalı, daha sonra uygun kalınlıkta uygulama yapılmalıdır. Tatbikat sıcaklığı +5 ile +35 °C arasında olmalıdır.

KURUMA SÜRELERİ (20 °C)

Dokunma Kuruması: 40-50 dk
Montaj Kuruması: 2-3 saat
Tam Kuruma: 24 saat

İNCELTME

Poliüretan tiner ile %15-20 oranında inceltilir. Uygulama için hazırlanan karışım 4-6 saat içinde bitirilmelidir.

BOYANABİLEN ALAN

Yaklaşık olarak 9-10 m²/lt (50 mikron uygulamada) alan boyanır.

PROPERTIES

Looking bright, smooth surface, high covering capacity power, chemicals, scratch and impact resistant.

AREAS OF USE

Yellowing resistant finish furniture furniture. Veneer, MDF, solid wood, parquet, nexus and furniture industry shows in high performance.

APPLICATION

To achieve a good adhesion to the surface must be cleaned completely. Oil, rust and dirt must be cleared with the appropriate cleaning of materials. Prepared surface by weight 3 units A Comp. /1 Unit B comp. mixed in such a way. Prepared mixture for the application 4-6 must be completed whether or not within the hour. Application will be made in the form of a powder to the surface before paint application has to be done, then it should be made on the implementation of the appropriate thickness. Exercise temperature should be between + 5 and + 35 ° c.

DRYING PERIOD (20°C)

Set to Touch Drying: 40-50 minutes
Montage Drying: 2-3 Hours
Hard Drying: 24 Hours

THINNING(VOLUME)

15-20% with polyurethane thinner. Prepared mixture for the application 4-6 must be completed within the hour.

COVERAGE

Approximately 9-10 m²/lt (50 mc single coat)



ÇİFT BİLEŞENLİ, ALİFATİK İSOSİYANAT KÜRLEMELİ, SARARMAYAN, UV DAYANIMI YÜKSEK , KOLAY UYGULANABİLEN,İYİ YAPIŞAN VE YAYILAN POLİÜRETAN REÇİNE ESASLI ASTAR BOYADIR.

TWO COMPENANT, THE CURED ALIPHATIC İSOSİYANAT, HIGH UV RESISTANCE, EASY TO IDENTIFY APPLICABLE, GOOD ADHESIVE AND SPREAD POLYURETHANE RESIN BASED PRİMER PAINT.