

TEK BİLEŞENLİ AKRİLİK SONKAT BOYA

ONE COMPENANT ACRYLIC TOPCOAT PAINT



TEK BİLEŞENLİ, HIZLI YÜZEY KURUMASI YAPABİLEN, AKRİLİK REÇİNE ESASLI SON KAT BOYADIR.

ONE COMPENANT, FAST SURFACE DRYING, ACRYLIC RESIN BASED AIR DRYING TOPCOAT PAINT

ÖZELLİKLERİ

Yüzeye çok iyi yapışır. Çok iyi kuruma yapar. Parlak ve endüstriyel hava şartlarına, tuza ve benzine karşı dayanıklıdır.

KULLANIM ALANLARI

Endüstriyel akrilik sonkat her türlü araç üstü ekipman ve tarım makineleri gibi çeşitli makine imalatları ile çelik konstrüksiyon metal yüzeyleri boyamada sonkat boya olarak kullanılır.

UYGULAMA

Uygulanacak yüzeyler temiz, kuru ve kirden arındırılmış olmalıdır. Eski boyalar kazınarak temizlenmelidir. Uygulama için sprey tabancası ve pistole kullanılabilir. Hava sıcaklığı 5°C ile 50°C arasında, uygulanacak zemin sıcaklığı +10°C ve +30°C arasında, Relatif Nem <85% olmalıdır.

KURUMA SÜRESİ (20 °C)

Dokunma Kuruması: 10-12 dk
Montaj Kuruması: 2-4 saat
Tam Kuruma: 24 saat

İNCELTME

Akrilik tiner ile %20 oranında inceltilir.

BOYANABİLEN ALAN

Yaklaşık olarak 10-12 m²/kg (50-60mc. kuru film kalınlığı verecek şekilde)

PROPERTIES

It has a very good adhesion surfaces. It has fast drying. It has industrial weather resistant, salt and gasoline.

AREAS OF USE

Industrial acrylic primer is applicable all type of machinery, tractor, trailer etc. It can be applied every metal surfaces.

APPLICATION

All surfaces must be sound, clean, dry. The old paints must be scraped and removed. It can be used with spry gun, pistole, brush or roller. Air temperature must be at min +5°C max +50°C. Surface temperature must be at min +10°C max +30°C temperature. Relative humidity must be <85%

DRYING PERIOD (20°C)

Set to Touch Drying: 10-12 minutes
Montage Drying: 2-4 Hours
Hard Drying: 24 Hours

THINNING(VOLUME)

20% with acrylic thinner

COVARAGE

Approximately 10-12 m²/kg (50-60 mc single coat)

İKİ BİLEŞENLİ AKRİLİK PARLAK BOYA

TWO COMPENANT ACRYLIC GLOSS PAINT



ÇİFT BİLEŞENLİ, HIZLI YÜZEY KURUMASI YAPABİLEN VE ALİFATİK İSOSİYANAT SERTLEŞTİRİCİSİ İLE KÜRLENEN, UV DAYANIMI YÜKSEK, AKRİLİK REÇİNE ESASLI PARLAK BOYADIR.

TWO COMPENANT, FAST SURFACE DRYING AND THE CURED WITH ALIPHATIC HARDENER İSOSİYANAT, HIGH UV RESISTANCE, ACRYLIC RESIN BASED AIR DRYING GLOSSY PAINT

ÖZELLİKLERİ

UV dayanımı istenen ahşap ve metal yüzeylerin korunması için geliştirilmiştir. Genel sanayi, makine üreticileri, metal korunumunda, çelik konstrüksiyon boyamalarında ve marin uygulamalarında performansı çok iyidir.

KULLANIM ALANLARI

Son kat boya sistemlerinin altına uygulanarak boya sisteminin dayanıklılığını arttırmak ve son katın daha parlak olmasını sağlamak için kullanılır.

UYGULAMA

Hazırlanan yüzeye ağırlıkça 3 Birim A Komp. /1 Birim B Komp. olacak şekilde karıştırılır. Uygulama için hazırlanan karışım 5-7 saat içinde kullanılıp bitirilmelidir. Tatbikat sıcaklığı +5 ile +35 °C arasında olmalıdır.

KURUMA SÜRELERİ (20 °C)

Dokunma Kuruması: 7-20 dk
Montaj Kuruması: 2-4 saat
Tam Kuruma: 24 saat

İNCELTME

Akrilik tiner ile %20-30 oranında inceltilir.

BOYANABİLEN ALAN

Yaklaşık olarak 9-10 m²/lt (30-50 mc. kuru film kalınlığı verecek şekilde) tek kat olarak uygulanır.

PROPERTIES

UV resistance has been developed for the protection of wood and metal surface requested. General industry, machinery manufacturers, metal dyeing of the steel construction, conservation and marine applications, performance is very good.

AREAS OF USE

To achieve a good adhesion to the surface must be cleaned completely. Oil, rust and dirt must be cleared with the appropriate cleaning of materials. Surface sanded paint that is suitable for. Top coat paint systems to increase the durability of the system by applying the paint to the bottom and is used to ensure that the last floor is brighter.

APPLICATION

Prepared surface by weight 3 Unit A Komp. /1 Unit B comp. mixed in such a way. Prepared mixture for the application 5-7 must be completed whether or not within the hour. Application will be made in the form of a powder to the surface before paint application has to be done, then it should be made on the implementation of the appropriate thickness. Exercise temperature should be between + 5 and + 35 °C.

DRYING PERIOD (20°C)

Set to Touch Drying: 7-20 minutes
Montage Drying: 6 Hours
Hard Drying: 24 Hours

THINNING (VOLUME)

20-30% with acrylic thinner

COVARAGE

Approximately 9-10 m²/lt (30-50 mc single coat) is implemented as a single layer.

AKRİLİK YARI MAT BOYA

ACRYLIC SEMIDULL PAINT

ÖZELLİKLERİ

Özellikle atmosfere açık alanlarda, uv dayanımı istenen ahşap ve metal yüzeylerin korunması için geliştirilmiştir.

KULLANIM ALANLARI

Genel sanayi, makine üreticileri, metal korunumunda, çelik konstrüksiyon boyamalarında ve marin uygulamalarında performansı çok iyidir.

UYGULAMA

Hazırlanan yüzeye ağırlıkça 3 Birim A Komp. /1 Birim B Komp. olacak şekilde karıştırılır. Uygulama için hazırlanan karışım 5-7 saat içinde kullanılıp bitirilmelidir. Tatbikat sıcaklığı +5 ile +35 °C arasında olmalıdır.

KURUMA SÜRELERİ (20 °C)

Dokunma Kuruması: 10-12 dk
Montaj Kuruması: 2-4 saat
Tam Kuruma: 24 saat

İNCELTME

Akrilik tiner ile %20 oranında inceltililebilir.

BOYANABİLEN ALAN

Yaklaşık olarak 10-12 m²/lt (30-50 mc. kuru film kalınlığı verecek şekilde)

PROPERTIES

Especially in public areas, atmosphere, uv resistance has been developed for the protection of wood and metal surface requested.

AREAS OF USE

General industry, machinery manufacturers, metal dyeing of the steel construction, conservation and marine applications, performance is very good.

APPLICATION

Prepared surface by weight 3 Unit A Komp. /1 Unit B comp. mixed in such a way. Prepared mixture for the application 5-7 must be completed whether or not within the hour. Exercise temperature should be between + 5 and + 35 °C.

DRYING PERIOD (20°C)

Set to Touch Drying: 10-12
Montage Drying: 6 Hours
Hard Drying: 24 Hours

THINNING(VOLUME)

20% with acrylic thinner

COVERAGE

Approximately 10-12 m²/lt (30-50 mc single coat)



ÇİFT BİLEŞENLİ, HIZLI YÜZEY KURUMASI YAPABİLEN VE ALİFATİK İSOSİYANAT SERTLEŞTİRİCİSİ İLE KÜRLENEN, UV DAYANIMI YÜKSEK, AKRİLİK REÇİNE ESASLI YARI MAT BOYADIR.

TWO COMPENANT, FAST SURFACE DRYING AND THE CURED WITH ALIPHATIC HARDENER İSOSİYANAT, HIGH UV RESISTANCE, ACRYLIC RESIN BASED SEMIDULL PAINT

AKRİLİK ASTAR BOYA

ACRYLIC PRIMER PAINT

ÖZELLİKLERİ

UV dayanımı istenen ahşap ve metal yüzeylerin korunması için geliştirilmiştir. Genel sanayi, makine üreticileri, metal korunumunda, çelik konstrüksiyon boyamalarında ve marin uygulamalarında performansı çok iyidir.

KULLANIM ALANLARI

Son kat boya sistemlerinin altına uygulanarak boya sisteminin dayanıklılığını arttırmak ve son katın daha parlak olmasını sağlamak için kullanılır.

UYGULAMA

Hazırlanan yüzeye ağırlıkça 3 Birim A Komp. /1 Birim B Komp. olacak şekilde karıştırılır. Uygulama için hazırlanan karışım 5-7 saat içinde kullanılıp bitirilmelidir. Uygulama yapılacak yüzeye önce bir toz şeklinde boya uygulaması yapılmalı, daha sonra uygun kalınlıkta uygulama yapılmalıdır. Tatbikat sıcaklığı +5 ile +35 °C arasında olmalıdır.

KURUMA SÜRELERİ (20 °C)

Dokunma Kuruması: 7-20 dk
Montaj Kuruması: 2-4 saat
Tam Kuruma: 24 saat

İNCELTME

Akrilik tiner ile %20-30 oranında inceltililebilir.

BOYANABİLEN ALAN

Yaklaşık olarak 9-10 m²/lt (30-50 mc. kuru film kalınlığı verecek şekilde) tek kat olarak uygulanır.

PROPERTIES

UV resistance has been developed for the protection of wood and metal surface requested. General industry, machinery manufacturers, metal dyeing of the steel construction, conservation and marine applications, performance is very good.

AREAS OF USE

Top coat paint systems to increase the durability of the system by applying the paint to the bottom and is used to ensure that the last floor is brighter.

APPLICATION

Prepared surface by weight 3 Unit A Komp. /1 Unit B comp. mixed in such a way. Prepared mixture for the application 5-7 must be completed whether or not within the hour. Application will be made in the form of a powder to the surface before paint application has to be done, then it should be made on the implementation of the appropriate thickness. Exercise temperature should be between + 5 and + 35 °C.

DRYING PERIOD (20°C)

Set to Touch Drying: 7-20 minutes
Montage Drying: 6 Hours
Hard Drying: 24 Hours

THINNING(VOLUME)

20-30% with acrylic thinner

COVERAGE

Approximately 9-10 m²/lt (30-50 mc single coat) is implemented as a single layer.



ÇİFT BİLEŞENLİ, HIZLI YÜZEY KURUMASI YAPABİLEN VE ALİFATİK İSOSİYANAT SERTLEŞTİRİCİSİ İLE KÜRLENEN, UV DAYANIMI YÜKSEK, AKRİLİK REÇİNE ESASLI ASTAR BOYADIR.

TWO COMPENANT, FAST SURFACE DRYING AND THE CURED WITH ALIPHATIC HARDENER İSOSİYANAT, HIGH UV RESISTANCE, ACRYLIC RESIN BASED AIR DRYING PRIMER PAINT