

AKRİLİK YARI MAT BOYA

ACRYLIC SEMIDULL PAINT

ÖZELLİKLERİ

Özellikle atmosfere açık alanlarda, uv dayanımı istenen ahşap ve metal yüzeylerin korunması için geliştirilmiştir.

KULLANIM ALANLARI

Genel sanayi, makine üreticileri, metal korunumunda, çelik konstrüksiyon boyamalarında ve marin uygulamalarında performansı çok iyidir.

UYGULAMA

Hazırlanan yüzeye ağırlıkça 3 Birim A Komp. /1 Birim B Komp. olacak şekilde karıştırılır. Uygulama için hazırlanan karışım 5-7 saat içinde kullanılıp bitirilmelidir. Tatbikat sıcaklığı +5 ile +35 °C arasında olmalıdır.

KURUMA SÜRELERİ (20 °C)

Dokunma Kuruması: 10-12 dk
Montaj Kuruması: 2-4 saat
Tam Kuruma: 24 saat

İNCELTME

Akrilik tiner ile %20 oranında inceltililebilir.

BOYANABİLEN ALAN

Yaklaşık olarak 10-12 m²/lt (30-50 mc. kuru film kalınlığı verecek şekilde)

PROPERTIES

Especially in public areas, atmosphere, uv resistance has been developed for the protection of wood and metal surface requested.

AREAS OF USE

General industry, machinery manufacturers, metal dyeing of the steel construction, conservation and marine applications, performance is very good.

APPLICATION

Prepared surface by weight 3 Unit A Komp. /1 Unit B comp. mixed in such a way. Prepared mixture for the application 5-7 must be completed whether or not within the hour. Exercise temperature should be between + 5 and + 35 °C.

DRYING PERIOD (20°C)

Set to Touch Drying: 10-12
Montage Drying: 6 Hours
Hard Drying: 24 Hours

THINNING(VOLUME)

20% with acrylic thinner

COVERAGE

Approximately 10-12 m²/lt (30-50 mc single coat)



ÇİFT BİLEŞENLİ, HIZLI YÜZEY KURUMASI YAPABİLEN VE ALİFATİK İSOSİYANAT SERTLEŞTİRİCİSİ İLE KÜRLENEN, UV DAYANIMI YÜKSEK, AKRİLİK REÇİNE ESASLI YARI MAT BOYADIR.

TWO COMPENANT, FAST SURFACE DRYING AND THE CURED WITH ALIPHATIC HARDENER İSOSİYANAT, HIGH UV RESISTANCE, ACRYLIC RESIN BASED SEMIDULL PAINT

AKRİLİK ASTAR BOYA

ACRYLIC PRIMER PAINT

ÖZELLİKLERİ

UV dayanımı istenen ahşap ve metal yüzeylerin korunması için geliştirilmiştir. Genel sanayi, makine üreticileri, metal korunumunda, çelik konstrüksiyon boyamalarında ve marin uygulamalarında performansı çok iyidir.

KULLANIM ALANLARI

Son kat boya sistemlerinin altına uygulanarak boya sisteminin dayanıklılığını arttırmak ve son katın daha parlak olmasını sağlamak için kullanılır.

UYGULAMA

Hazırlanan yüzeye ağırlıkça 3 Birim A Komp. /1 Birim B Komp. olacak şekilde karıştırılır. Uygulama için hazırlanan karışım 5-7 saat içinde kullanılıp bitirilmelidir. Uygulama yapılacak yüzeye önce bir toz şeklinde boya uygulaması yapılmalı, daha sonra uygun kalınlıkta uygulama yapılmalıdır. Tatbikat sıcaklığı +5 ile +35 °C arasında olmalıdır.

KURUMA SÜRELERİ (20 °C)

Dokunma Kuruması: 7-20 dk
Montaj Kuruması: 2-4 saat
Tam Kuruma: 24 saat

İNCELTME

Akrilik tiner ile %20-30 oranında inceltililebilir.

BOYANABİLEN ALAN

Yaklaşık olarak 9-10 m²/lt (30-50 mc. kuru film kalınlığı verecek şekilde) tek kat olarak uygulanır.

PROPERTIES

UV resistance has been developed for the protection of wood and metal surface requested. General industry, machinery manufacturers, metal dyeing of the steel construction, conservation and marine applications, performance is very good.

AREAS OF USE

Top coat paint systems to increase the durability of the system by applying the paint to the bottom and is used to ensure that the last floor is brighter.

APPLICATION

Prepared surface by weight 3 Unit A Komp. /1 Unit B comp. mixed in such a way. Prepared mixture for the application 5-7 must be completed whether or not within the hour. Application will be made in the form of a powder to the surface before paint application has to be done, then it should be made on the implementation of the appropriate thickness. Exercise temperature should be between + 5 and + 35 °C.

DRYING PERIOD (20°C)

Set to Touch Drying: 7-20 minutes
Montage Drying: 6 Hours
Hard Drying: 24 Hours

THINNING(VOLUME)

20-30% with acrylic thinner

COVERAGE

Approximately 9-10 m²/lt (30-50 mc single coat) is implemented as a single layer.



ÇİFT BİLEŞENLİ, HIZLI YÜZEY KURUMASI YAPABİLEN VE ALİFATİK İSOSİYANAT SERTLEŞTİRİCİSİ İLE KÜRLENEN, UV DAYANIMI YÜKSEK, AKRİLİK REÇİNE ESASLI ASTAR BOYADIR.

TWO COMPENANT, FAST SURFACE DRYING AND THE CURED WITH ALIPHATIC HARDENER İSOSİYANAT, HIGH UV RESISTANCE, ACRYLIC RESIN BASED AIR DRYING PRIMER PAINT